

 **SHINKONG™ 新光合成纖維股份有限公司****SHINKONG SYNTHETIC FIBERS CORPORATION**台北市南京東路二段 123 號 14 樓
14TH FL, 123, SEC. 2, NANKING E. ROAD, TAIPEI, TAIWAN, R. O. C.

SHINPET 5015X

TECHNICAL SPECIFICATION

PROPERTY	UNIT	VALUE	TEST METHOD
I. V.	d l / g	0.84 ± 0.02	ASTM D-2857
H ₂ O CONTENT	wt %	<0.5	ASTM D-6869
MELTING POINT	°C	246 ± 4	ASTM D-3418
COLOR (b)		0.0 ± 2.0	JIS Z 8722
PELLET SHAPE		OVAL	
BULK DENSITY	g / cm ³	0.9 ± 0.1	
PACKING	Kg / BAG	1, 100	
A. A. CONTENT	ppm	<1.0	CELANESE

•NOTE: RECOMMENED DRYING TEMP. / TIME

160 ~ 170 °C / 5 ~ 7 hours

Properties reported here are typical of average lots. Makes no representation that the material in any particular shipment will conform exactly to the values given. Neither SSFC nor its marketing affiliates shall be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.