

Technical Data Sheet

Manufacturer:

SASA Polyester Sanayi A.S.

Grade:

SASA PET BG-84™

Brand:

ADVANITE™

Specifications:

Properties	Test Results	Specification	Methods
B-1. INTRINSIC VISCOSITY (dL/Gr)	0.828	0.840 ± 0.020	ASTM D4603
B-2. "L*" COLOUR (CIE LAB)	81.2	Min 80	ASTM D6290
B-3. "b*" COLOUR (CIE LAB)	-0.9	Max 1	ASTM D6290
B-4. ACETALDEHYDE (ppm)	0.8	Max 1	ASTM F2013
B-5. CHIP SIZE (Gr/100 CHIPS)	1.60	1.60 ± 0.20	SASA Internal Method
B-6. MELTING POINT (°C)	247,9	248 ± 3	ASTM D3418
B-7. MOISTURE CONTENT (%)	0.03	Max 0.2	ASTM D6869

Disclaimer: This document is for information purposes only. Customers are responsible for testing and confirming the suitability of this product in their application. To the extent permitted by law, no warranty as to merchantability or fitness of purpose, expressed or implied, is made.

GLOBAL OFFICES

USA

2106 House Ave, Suite 712,
Cheyenne, Wyoming 82001, USA

SINGAPORE

20 Collyer Quay, #09-01,
Singapore 049319

UAE

Shams Business Center, Al Messaned,
Sharjah, UAE

PAKISTAN

T1 Horizon Tower, Com 2/6, Khayaban
-e-Saadi, Block 3 Clifton, Karachi, Pakistan

Technical Data Sheet

Document Details:

Document No: SPC-PS-005

Revision Date: 10.10.2011

Revision No: 1

A. General:

A-1. Values shown below are the average test results that are performed per SASA s relevant test methods on the day of production.

Batch Details:

A-2. Production Date : 29.07.2024

A-3. Lot No : 1000003946

A-4. Net Weight : 5 KG

Disclaimer: This document is for information purposes only. Customers are responsible for testing and confirming the suitability of this product in their application. To the extent permitted by law, no warranty as to merchantability or fitness of purpose, expressed or implied, is made.

GLOBAL OFFICES

USA

2106 House Ave, Suite 712,
Cheyenne, Wyoming 82001, USA

SINGAPORE

20 Collyer Quay, #09-01,
Singapore 049319

UAE

Shams Business Center, Al Messaned,
Sharjah, UAE

PAKISTAN

T1 Horizon Tower, Com 2/6, Khayaban
-e-Saadi, Block 3 Clifton, Karachi, Pakistan