

Technical Data Sheet

Manufacturer:**Shinkong Synthetic Fibers Corporation****Product:****Bottle Grade PET Resin****Grade:****SHINPET 5015W****Specifications:**

Property	Unit	Value	Test Method
I.V.	dL/g	0.80 ± 0.02	ASTM D-2857
H ₂ O Content	wt %	< 0.5	ASTM D-6869
Melting Point	°C	246 ± 4	ASTM D-3418
Color (b)		0.0 ± 2.0	JIS Z 8722
Pellet Shape		OVAL	
Bulk Density	g/cm ³	0.9 ± 0.1	
Packing	kg/bag	1,100	
A.A. Content	ppm	< 1.0	CELANESE

Recommended Drying Temperature / Time:**160 ~ 170°C / 5 ~ 7 hours**

Disclaimer: This document is for information purposes only. Customers are responsible for testing and confirming the suitability of this product in their application. To the extent permitted by law, no warranty as to merchantability or fitness of purpose, expressed or implied, is made.

GLOBAL OFFICES**USA**

2106 House Ave, Suite 712,
Cheyenne, Wyoming 82001, USA

SINGAPORE

20 Collyer Quay, #09-01,
Singapore 049319

UAE

Shams Business Center, Al Messaned,
Sharjah, UAE

PAKISTAN

T1 Horizon Tower, Com 2/6, Khayaban
-e-Saadi, Block 3 Clifton, Karachi, Pakistan

Technical Data Sheet

Manufacturer Note:

Properties reported here are typical of average lots. Makes no representation that the material in any particular shipment will conform exactly to the values given. Neither SSFC nor its marketing affiliates shall be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

Manufacturer Details:

Shinkong Synthetic Fibers Corporation

Disclaimer: This document is for information purposes only. Customers are responsible for testing and confirming the suitability of this product in their application. To the extent permitted by law, no warranty as to merchantability or fitness of purpose, expressed or implied, is made.

GLOBAL OFFICES

USA

2106 House Ave, Suite 712,
Cheyenne, Wyoming 82001, USA

SINGAPORE

20 Collyer Quay, #09-01,
Singapore 049319

UAE

Shams Business Center, Al Messaned,
Sharjah, UAE

PAKISTAN

T1 Horizon Tower, Com 2/6, Khayaban
-e-Saadi, Block 3 Clifton, Karachi, Pakistan